


binderholz 3/MULTIPLY SOLID WOOD PANEL □

STRUCTURE

3 ply solid wood panel



Technical data	
Wood species	Spruce, larch, douglas, scots pine, swiss pine
Gluing	DIN 68705 part 2 AW 100 – ÖNORM B 3022 type VF
CE certification	EPH Dresden to EN 13986 SWP/2 and SWP3/ L3
Panel format	5000 – 6000 x 1250 mm
Panel thickness	16, 19, 22, 27, 32, 40, 42, 50, 60 mm – other thicknesses on request
Lamella width	approx. 120 mm
Sorting quality	ÖNORM B3021, EN 13017-1
Surface	sanded on both sides K 80
Moisture content	8 % ex factory
Qualities	O/B, A/B, B/C+, B/C, C+/C+, C+/C, C/C

Technical modification without prior notice.

Binderholz GmbH • Massivholzplattenwerk
Gewerbegebiet 2 ▪ A-5113 St. Georgen bei Salzburg
fon +43 6272 8511 ▪ fax +43 6272 8511-95
st.georgen@binderholz.com ▪ www.binderholz.com

