

Product Data Sheet

| | |
|----------------------------|-------------------------|
| Dimensions | 1900x 190x 15(4)mm |
| Pieces per pack | 8 |
| Overall thickness | 15mm |
| m2 per pack | 2,166m2 |
| Percentage of short boards | 18,80% |
| Package design | box/package with design |

| | |
|---------------------|--------------------------------------------------------------------------|
| Construction | |
| Surface layer | Larch 4mm |
| Core layer | Pine 7mm |
| Back layer | Larch 4mm |
| T&G or click | T&G with bevel on 4sides |
| Moisture content | 7% ± 2 |
| Grading | AB |
| Finishing | Lacquered |
| Brand of lacquer | Treffert |
| Wear resistance | test result from factory Falling sand 2000 circles 175# sand paper |
| Stain resistance | test result from factory Class 5 |
| Color of filler | Wood color |

| | |
|---------------------|--------------------------|
| Installation | Floating or Glue down |
|---------------------|--------------------------|

| | |
|-----------|---------------|
| CE | EN 14342:2013 |
|-----------|---------------|

| | |
|---------------------------------|----------|
| Aspect | |
| Lipping - differences in height | ≤ 0.15mm |
| Difference in length | ± 1.0mm |
| Difference in width | ± 0.15mm |
| Cupping lengthwise | ≤ 0.2% |
| Cupping in width | ≤ 0.1% |

| | | |
|------------------------|--------------------------|----------|
| Slip resistance | test result from factory | USRV 100 |
|------------------------|--------------------------|----------|

| | | |
|---------------------------------|------------|--------------------|
| Emission of Formaldehyde | (EN 717-1) | ≤ 0.124mg/m3 E1 |
|---------------------------------|------------|--------------------|

| | | |
|------------|--------------|--------|
| PCP | CEN/TR 14823 | ≤ 5ppm |
|------------|--------------|--------|

| | | |
|-----------------------------|--------------------------|------------|
| Thermal conductivity | test result from factory | 0.14 W/m2K |
|-----------------------------|--------------------------|------------|

| | | |
|------------------------------|-----------|---------|
| Biological Durability | (EN335-1) | Class 1 |
|------------------------------|-----------|---------|

| | | |
|-------------------------|--------------|--------|
| Reaction to fire | (EN 13501-1) | Df1-s1 |
|-------------------------|--------------|--------|