

Product Data Sheet

Dimensions	1860x189x14mm
Pieces per pack	8
Quantity m2 per pack	2.81232m2
Percentage of short boards	18,80%
Package design	package with design

Construction	3-layer
Top layer	Oak 3mm
Core layer	Poplar 9mm
Back layer	Poplar 2mm
Brand of Glue	Dynea
T&G or Click	T&G with 0.5mm bevel on 4sides
Moisture content	7% ± 2
Grading	ABC
Finishing	Brushed, Matt Lacquered
Brand of lacquer	Bergolin Germany
Wear resistance	test result from fatory Falling sand 1500 circles 175# sand paper
Stain resistance	test result from fatory Class 5
Color of filler	Wood color

Installation	Floating or Glue down
---------------------	--------------------------

CE	EN 14342:2013
-----------	---------------

Aspect	
Lipping - differences in height	≤ 0.15mm
Difference in length	± 1.0mm
Difference in width	± 0.15mm
Cupping lengthwise	≤ 0.2%
Cupping in width	≤ 0.1%

Slip resistance	test result from fatory	USRV 100
------------------------	-------------------------	----------

Emission of Formaldehyde	(EN 717-1)	≤ 0.124mg/m3 E1
---------------------------------	------------	--------------------

PCP	CEN/TR 14823	≤ 5ppm
------------	--------------	--------

Thermal conductivity	test result from fatory	0.14 W/m2K
-----------------------------	-------------------------	------------

Biological Durability	(EN335-1)	Class 1
------------------------------	-----------	---------

Reaction to fire	(EN 13501-1)	Df1-s1
-------------------------	--------------	--------